

DEKRA Automobil GmbH Handwerkstr. 15 D-70565 Stuttgart

Kambukka bvba
Stijn Lowette
Torenplein 7.16.1

3500 Hasselt
Belgium

DEKRA Automobil GmbH
Laboratory for Environmental & Product Analysis
Handwerkstr. 15
70565 Stuttgart
Tel. +49.711.7861-3548
Fax +49.711.7861-3534

Contact:
Ingo Kesselring
Telephone 0711/7861-3722
E-mail ingo.kesselring@dekra.com
Date 22.05.2013
Page 1 of 5

Test Report No.: 55245278/13

Project No.: 55245278

Client: Kambukka bvba
Stijn Lowette
Torenplein 7.16.1

3500 Hasselt
Belgium

Date of order: 03.05.2013

Sample received: 06.05.2013

Number of samples: 1 sample

Article description: Contigo, drinking bottle, „Trekker“, orange

Scope of investigation: Testing of consumer goods

Testing Period: 06.05.2013 – 22.05.2013

Test Result:

- following page / pages -

Accredited Analytical Laboratory D-PL-11060-03-00 in Stuttgart and Halle (Saale).

Sample No.:	55245278001			
Sample designation:	Contigo, drinking bottle, „Trekker“, orange (complete product)			
Sample description:	commodity			
Parameter	Unit	Result	LQ	Method
Sensorical test ^{1,2}	-	1	-	Acc. to DIN 10 955
Global migration: 3% acetic acid ³	mg/dm ²	1,0	0,1	Annex III of Reg. (EU)10/ 2011
Global migration: 50 % ethanol ³	mg/dm ²	0,9	0,1	
Primary aromatic amines ⁴	mg/ L	< LQ	0,002	§ 64 LFGB L 00.00-6
Specific migration of metals ⁴				
Barium	mg/ L	< LQ	0,01	(EU) 10/2011 EN ISO 11885
Cobalt	mg/ L	< LQ	0,01	
Copper	mg/ L	< LQ	0,01	
Iron	mg/ L	0,07	0,01	
Lithium	mg/ L	< LQ	0,01	
Manganese	mg/ L	0,01	0,002	
Zinc	mg/ L	< LQ	0,01	
Heavy metals – plastic material of bottle (orange, transparent)				
Cadmium	mg/kg	< LQ	2	EN ISO 11885
Lead	mg/kg	< LQ	10	
Heavy metals – mixed sample of lid (6 different materials)				
Cadmium	mg/kg	< LQ	2	EN ISO 11885
Lead	mg/kg	< LQ	10	

¹ Scale of intensity

- 0 - no noticeable change of smell and taste
- 1 - marginal change of smell and taste
- 2 - slight change of smell and taste
- 3 - clear change of smell and taste
- 4 - strong change of smell and taste

² Testing conditions: drinking water, 24 hours at 40°C³ Testing conditions: 2 hours at 70°C⁴ Testing conditions: 3% acetic acid, 24 hours at 40°C**Product foto:**

Resume:

According to §2 subsection 6 no.1 of the German Food and Feed Code (LFGB) the tested sample is a food contact article.

According to article 3 subsection 1 c of the regulation (EC) 1935/2004 materials and articles shall be manufactured in compliance with good manufacturing practise so that, under normal or foreseeable conditions of use, they do not transfer their constituents to food in quantities which could bring about a deterioration in the organoleptic characteristics thereof.
The tested sample meets this requirement.

According to article 12 (1) of the regulation (EU) 10/2011 plastic materials and articles shall not transfer their constituents to food simulants in quantities exceeding 10 milligrams per dm².
The sample keeps this limit for all tested simulants.

The sample meets the limit values for the migration of metals with according to annex II of the Regulation (EU) 10/2011 on plastic materials and articles intended to come into contact with food.

According to article 10 combined with annex II of the regulation (EU) 10/2011 plastic materials and articles shall not release primary aromatic amines in a detectable quantity into food or food simulant (detection limit is 0,01 mg per kg of food or food simulant).
The tested extract of the tested sample meets this requirement.

In the tested samples no cadmium or lead was detected.

Hints:

The test results refer exclusively to the samples specified. A reproduction in excerpts of the test report must not be made without the written consent of the test laboratory. Samples will be stored according to QMH 2001.5.8 for max. 6 months (for exceptions and specific storage times see QMH 2001.5.8). This test report replaces the test report of the same Project number with an index reduced by 1.

Stuttgart, 2013/05/22

DEKRA Automobil GmbH
Laboratory for Environmental and Product Analysis

